



## Spivercem Trasparente

### 1. SPECIFICATIONS AND FIELDS OF EMPLOYMENT

Transparent and protective finish reviving for concrete, high alkali resistance. Its composition makes it particularly suitable for protection against carbonation, and the decoration of concrete structures, brick and stone materials for external and internal use.

### 2. COMPOSITION

Special acrylic emulsions, alkali resistant, Uv filters, additives.

### 3. METHOD OF APPLICATION

Remove any residual products used to facilitate the disarmament and brush the surface thoroughly in order to Remove all traces of dirt, loose parts. In a case where there is mold is should be treated with DETERGENTE REOSAN. Apply a coat of SPIVERCEM TRASPARENTE diluted 100% with water; after about 12 hours, apply two coats of undiluted SPIVERCEM TRASPARENTE leaving a minimum 6 hours between each application. Do not apply to surfaces where there has been established the presence of rising damp or seepage.

### 4. TECHNICAL DATA

**SPECIFIC WEIGHT:** 1,000 kg./Lt. +/-0,5%

**APPLICATION:** brush, roller, and spray

**VISCOSITY:** 40" – 50" Coppa Ford 4

**FILM ASPECT:** shiny transparent

**YIELD:** 10-15 m<sup>2</sup> / Lt according to the porosity of the support.

**PACKAGE:** Lt. 15 polyethylene cases available

**DRYING:** 1 hours to the touch at about 20 degrees 24 hours to dry completely at about 20 C°

**PRESERVATION:** 36 months in the intact packages away from temperature changes

**HS CODE:** 32091000

### ITEM OF SPECIFICATIONS

Decoration and protection of concrete structures exposed with transparent protective anti-carbonation and reviving based on special acrylic emulsions alkali-resistant, UV filter, additives, the type of SPIVERCEM TRASPARENTE by SPIVER S.r.l. with average consumption of 0.1 Lt / m<sup>2</sup>, price includes materials and installation, excluding scaffolding m<sup>2</sup> € .....

NB The above-mentioned data are susceptible of variations. Spiver Ltd. is not responsible for any negative result depending on the application of the product out of the Company's control and on the agents unrelated to the product quality



*Emotion with paint ...*

#### SPIVER s.r.l.

contrada Babbaurra S.S. 122

93100 Caltanissetta ( CL )

Tel. +39 0934 57 77 91 Fax +39 0934 58 87 95

[www.spiver.it](http://www.spiver.it) - [info@spiver.it](mailto:info@spiver.it)

**Scheda Tecnica: Spivercem Trasparente SP 025. Rev.1** La presente scheda annulla e sostituisce le precedenti